

LDPE Lupolen 2420 D

Product Description

Lupolen 2420 D is a non –additivated ,low density Polyethylene .It is delivered in pellet form.

Applications

- Bags & Pouches
- Bottles for Consumer Goods
- Shrink Film
- Blown Film
- Film

Processing Method

- Blown Film Injection
- Moulding Extrusion Blow
- Moulding

Features

Good Heat Seal, Optical, Good Processability, Good Melt Strength

| No | Property | Value | Units | Test Method |
|----|---|---------|-------------------|---------------|
| 1 | Density | 0.923 | g/cm ³ | ISO 1183 |
| 2 | Melt flow rate (MFR)(190°C/2.16Kg) | 0.25 | g/10 min | ISO 1133 |
| 3 | Tensile Modulus | 240 | MPa | ISO 527-1, -2 |
| 4 | Tensile Stress at Yield | 10 | MPa | ISO 527-1, -2 |
| 5 | Tensile Strength MD/TD | 27/20 | MPa | ISO 527-1, -3 |
| 6 | Tensile Strain at Break MD/TD | 200/500 | % | ISO 527-1, -3 |
| 7 | Dart Drop Impact(50 blown film) | 250 | g | ASTM D 1709 |
| 8 | Vicat softening temp(A50 (50 °C/h 10N)) | 94 | °C | ISO 306 |
| 9 | Haze (50) | <14 | % | ASTM D 1003 |
| 10 | Gloss (60 °,50) | >50 | | ASTM D 2457 |

