

HD -I3

License Grade Code HC 7260(THE)

1) Product Description :

“I3” is a high density polyethylene with 1-Butene as co monomer .It is rigid, low warpage, good flowability, high density, hardness and stiffness, good impact strength good stress cracking resistance.

2) Applications:

- Injection moulding
- Crates
- Engineering parts
- Closures

3) Typical data

PROPERTY	TEST METHOD	UNIT	TYPICAL VALUE*
Mass density (23oC)	ISO 1183	g/cm ³	0.957
Melt Flow Rate (190oC/2.16kg)	ISO 1133	g/10min	8
Melt Flow Rate (190oC/5 kg)	ISO 1133	g/10min	23
Stress at Yield	ISO 527	MPa	29
Flexural Creep Modulus (4point, 1min)	DIN 19537-2	MPa	1550
Tensile Modulus (23oC, v = 1mm/min,Secant)	ISO 527	MPa	1350
Stress at Break	ISO 527	MPa	30
Elongation at Break	ISO 527	%	>1000
Elongation at yield	ISO 527	%	10
Softening Temperature	ISO 306	oC	72
Brittle Temperature	ASTM D746-72	oC	< - 80
Shore D hardness	ISO 868	-	64
ESCR in Full Notch Creep Test (80oC, 2% Arcopal)	ISO CD 16770	h@2.5 MPa	1.5
Impact strength (23oC)	ISO 179/1eA	Kj/m ²	2.5

4)Process condition:

Recommended injection molding temperature : °200 - 280 C
Licensor: Basell

Packing: 25 Kg plastic bag

